

Archive ouverte UNIGE

https://archive-ouverte.unige.ch

Article scientifique

Article 2014

Published version

Open Access

This is the published version of the publication, made available in accordance with the publisher's policy.

Nonlinear optical and magnetic properties of BiFeO₃ harmonic nanoparticles

Schwung, Sebastian; Rogov, Andrii; Clarke, Gareth; Joulaud, Cécile; Magouroux, Thibaud; Staedler, Davide; Passemard, Solène; Jüstel, Thomas; Badie, Laurent; Galez, Christine; Wolf, Jean-Pierre; Volkov, Yuri; Prina-Mello, Adriele; Gerber-Lemaire, Sandrine [**and 4 more**]

How to cite

SCHWUNG, Sebastian et al. Nonlinear optical and magnetic properties of BiFeO₃ harmonic nanoparticles. In: Journal of applied physics, 2014, vol. 116, n° 11, p. 114306. doi: 10.1063/1.4895836

This publication URL:https://archive-ouverte.unige.ch/unige:84332Publication DOI:10.1063/1.4895836

© This document is protected by copyright. Please refer to copyright holder(s) for terms of use.





Nonlinear optical and magnetic properties of BiFeO3 harmonic nanoparticles

Sebastian Schwung, Andrii Rogov, Gareth Clarke, Cécile Joulaud, Thibaud Magouroux, Davide Staedler, Solène Passemard, Thomas Jüstel, Laurent Badie, Christine Galez, Jean Pierre Wolf, Yuri Volkov, Adriele Prina-Mello, Sandrine Gerber-Lemaire, Daniel Rytz, Yannick Mugnier, Luigi Bonacina, and Ronan Le Dantec

Citation: Journal of Applied Physics **116**, 114306 (2014); doi: 10.1063/1.4895836 View online: http://dx.doi.org/10.1063/1.4895836 View Table of Contents: http://scitation.aip.org/content/aip/journal/jap/116/11?ver=pdfcov Published by the AIP Publishing

Articles you may be interested in

Effect of Dy-substitution on the structural, vibrational, and multiferroic properties of BiFeO3 nanoparticles J. Appl. Phys. **115**, 214109 (2014); 10.1063/1.4881529

Enhanced magnetic behavior, exchange bias effect, and dielectric property of BiFeO3 incorporated in (BiFeO3)0.50 (Co0.4Zn0.4Cu0.2 Fe2O4)0.5 nanocomposite AIP Advances **4**, 037112 (2014); 10.1063/1.4869077

Phase transition and magneto-electric coupling of BiFeO3–YMnO3 multiferroic nanoceramics J. Appl. Phys. **114**, 144104 (2013); 10.1063/1.4824061

Enhanced magnetic and dielectric properties of Eu and Co co-doped BiFeO3 nanoparticles Appl. Phys. Lett. **101**, 042401 (2012); 10.1063/1.4738992

Magnetic and dielectric properties of Eu-doped BiFeO3 nanoparticles by acetic acid-assisted sol-gel method J. Appl. Phys. **110**, 103905 (2011); 10.1063/1.3662178

Instruments for Advanced Science IDEN Gas Analysis Surface Science **Plasma Diagnostics** Contact Hiden Analytical for further details: Vacuum Analysis dynamic measurement of reaction gas streams partial pressure measurement and control www.HidenAnalytical.com ▶ UHV TPD plasma source characterization > catalysis and thermal analysis etch and deposition process reaction of process gases IMS INS ■ info@hiden.co.uk molecular beam studies > end point detection in ion beam etch kinetic studies ▹ reactive sputter process control vacuum diagnostics vacuum coating process monitoring dissolved species probes analysis of neutral and radical species > elemental imaging - surface mapping CLICK TO VIEW our product catalogue fermentation, environmental and ecological studies

This article is copyrighted as indicated in the article. Reuse of AIP content is subject to the terms at: http://scitation.aip.org/termsconditions. Downloaded to] IP: 129.194.8.73 On: Wed. 17 Sep 2014 07:51:56



Nonlinear optical and magnetic properties of BiFeO₃ harmonic nanoparticles

Sebastian Schwung,^{1,2} Andrii Rogov,³ Gareth Clarke,⁴ Cécile Joulaud,⁵ Thibaud Magouroux,³ Davide Staedler,⁶ Solène Passemard,⁶ Thomas Jüstel,² Laurent Badie,⁷ Christine Galez,⁵ Jean Pierre Wolf,³ Yuri Volkov,⁴ Adriele Prina-Mello,⁴ Sandrine Gerber-Lemaire,⁶ Daniel Rytz,¹ Yannick Mugnier,^{5,a)} Luigi Bonacina,^{3,a)} and Ronan Le Dantec⁵ ¹*FEE Gmbh, Struthstrasse 2, 55743 Idar-Oberstein, Germany* ²*Fachbereich Chemieingenieurwesen, Fachhochschule Münster, Stegerwaldstrasse 39, 48565 Steinfurt, Germany* ³*GAP-Biophotonics, Université de Genève, 22 Chemin de Pinchat, 1211 Genève 4, Switzerland* ⁴*Department of Clinical Medicine, Trinity College Dublin, Ireland* ⁵*Univ. Savoie, SYMME, F-74000 Annecy, France* ⁶*Institute of Chemistry and Chemical Engineering, Ecole Polytechnique Fédérale de Lausanne, Batochime (Bat BCH), CH-1015 Lausanne, Switzerland* ⁷*Institut Jean Lamour, UMR CNRS 7198, Faculté des Sciences et Techniques, Université de Lorraine, 54506 Vandoeuvre-lès-Nancy, France*

(Received 10 July 2014; accepted 5 September 2014; published online 16 September 2014)

Second Harmonic Generation (SHG) from BiFeO₃ nanocrystals is investigated for the first time to determine their potential as biomarkers for multiphoton imaging. Nanocrystals are produced by an auto-combustion method with 2-amino-2-hydroxymethyl-propane-1,3-diol as a fuel. Stable colloidal suspensions with mean particle diameters in the range 100–120 nm are then obtained after wet-milling and sonication steps. SHG properties are determined using two complementary experimental techniques, Hyper Rayleigh Scattering and nonlinear polarization microscopy. BiFeO₃ shows a very high second harmonic efficiency with an averaged $\langle d \rangle$ coefficient of 79 ± 12 pm/V. From the nonlinear polarization response of individual nanocrystals, relative values of the independent d_{ij} coefficients are also determined and compared with recent theoretical and experimental studies. Additionally, the particles show a moderate magnetic response, which is attributed to γ -Fe₂O₃ impurities. A combination of high nonlinear optical efficiency and magnetic response within the same particle is of great interest for future bio-imaging and diagnostic applications. © 2014 AIP Publishing LLC. [http://dx.doi.org/10.1063/1.4895836]

I. INTRODUCTION

Harmonic nanoparticles (HNPs) are new types of exogenous contrast agents, which have been recently proposed as biomarkers for multiphoton imaging.^{1–6} They are based on noncentrosymmetric nanocrystals where efficient bulk second harmonic generation (SHG) is allowed by the crystal symmetry. Due to the non-resonant nature of SHG, these biomarkers show very attractive properties for in vitro or in vivo imaging such as extreme photostability⁴ and excitation wavelength tunability.⁷ As underlined in recent reviews,^{8,9} HNPs can complement usual fluorescent probes (i.e., dyes or quantum dots) for specific demanding applications like regenerative medicine.

From a material point of view, ideal HNPs must have high nonlinear optical (NLO) properties, low cytotoxicity but also easy processing for an effective control of the nanoparticles size, shape, and surface properties. Up to now, various types of noncentrosymmetric nanoparticles have been produced, among which are numerous oxides such as Fe(IO₃)₃,¹⁰ LiNbO₃,^{11,12} KNbO₃,¹³ KTP,¹⁴ and BaTiO₃^{6,15} with typical diameters at about 100 nm or semiconductors like ZnO (Ref. 16) and CdTe.¹⁷ We showed in a recent comprehensive survey¹⁸ that the harmonic conversion efficiency of most of these nanoparticles is close to the value for the corresponding bulk materials and thus, the responses of the different oxide nanoparticles are relatively similar. Moreover, we demonstrated that these nanoparticles have low cytotoxicity with the exception of ZnO particles.¹⁸ Finally, it was demonstrated that CdTe¹⁷ quantum dots have noticeably higher intrinsic nonlinear efficiency but the known toxicity of these cadmium-based dots may appear as a limitation for in vivo applications.¹⁹

On the other hand, BiFeO₃ (BFO) is a widely investigated compound since it is, to date, the only known room temperature multiferroic material. Being extensively studied for its magnetoelectric behavior, BFO also has attractive ferroelectric properties with high spontaneous polarization.²⁰ Moreover, recent studies give evidences of a very promising nonlinear optical efficiency,^{21,22} which was found to be superior to the standard oxide materials previously introduced. Second, bulk BFO is antiferromagnetic but nanoparticles show weak ferromagnetism which was attributed to various possible causes: size effects,²³ extrinsic effects due to γ -Fe₂O₃ impurities,²⁴ or oxygen vacancies.²⁵

It is well-established that magnetic nanoparticles are essential for the biomedical field with key applications such as magnetic separation, Magnetic Resonance Imaging (MRI), or hyperthermia.²⁶ Accordingly, multifunctional

^{a)}Authors to whom correspondence should be addressed. Electronic mail addresses: yannick.mugnier@univ-savoie.fr and Luigi.Bonacina@unige.ch

BFO nanoparticles present a unique combination of potentially high nonlinear optical properties and magnetic characteristics, which make them promising for the targeted bio-imaging applications and possible therapeutic applications.²⁷

Here, we describe an extensive study on BFO nanoparticles preparation followed by nonlinear optical and magnetic characterization. BFO nanoparticles were produced by an original combustion synthesis with the aim of using a scalable production method and of lowering the annealing temperature. Indeed, to eliminate undesirable secondary phases during BFO preparation, the temperature must be high enough to form BiFeO3;28 but at the same time, it should stay low enough to prevent the thermal decomposition to $Bi_2Fe_4O_9$ and $Bi_{25}FeO_{39}^{29}$ or the partial reduction of Fe^{3+} to Fe^{2+} .³⁰ In addition, a low temperature process preventing particle growth by Ostwald ripening is desirable, an aspect which is generally important for the synthesis of nanocrystals. After the preparation step, Hyper Rayleigh Scattering (HRS) measurements and SHG microscopy were used to determine the second order nonlinear optical properties of the particles in order to evaluate their potential as HNPs. Finally, vibrating sample magnetometry was used to measure their magnetic response.

II. SYNTHESIS OF BFO NANOPARTICLES BY COMBUSTION METHOD

Different processes have been described for BFO preparation in the literature. Low process temperatures can be achieved by hydrothermal synthesis^{31,32} also combined with microwave assisted heating.³³ Another method is the polyol-mediated synthesis in poly-alcohols like ethylene glycol or diethylene glycol.^{23,34,35} However, these approaches remain undemonstrated for producing large amounts of material and a reduction of Fe³⁺ by oxidation of the polyol was also observed.³⁶ On the other hand, widely used methods for the preparation of nanocrystalline BFO are sol-gel reactions like chelate assisted or Pechini reactions with citric acid³⁷ or tartaric acid.^{38,39} As described in the original patent,⁴⁰ the Pechini method needs an annealing step to decompose the amorphous organic precursor and to promote crystallization.³⁹ A cross-linked network is indeed first produced where the metal ions are bonded to organic radicals by oxygen bonds.

With this in mind, the formation of a crystalline or partially crystalline precursor would appear to be a desirable improvement. For this purpose, the classical chelating agents can be substituted by the fuel 2-amino-2-hydroxymethyl-propane-1,3-diol (TRIS). Such combustion syntheses are known for oxide materials.⁴¹ Briefly, this method is based on the highly exothermic redox reaction between an oxidizing agent such as metal nitrates and a reducing agent, i.e., the fuel.⁴¹ During the ignition of the fuel, local temperatures can reach up to 2000 K.⁴² In the case of BFO, sucroseassisted synthesis has been described in the literature⁴³ where a stoichiometric amount of sucrose (fuel) was adapted to the metal ion concentration. The mixture was subsequently dried to a resin and auto-ignited on a magnetic stirrer. In another work on the auto-combustion synthesis of BFO, glycine⁴⁴ was used as a fuel.

The goal of the present work is to take advantage of the combustion method for the direct formation of a crystalline precursor of BFO following the first reaction step. With respect to standard sol-gel reactions, lower annealing temperatures can be expected to obtain phase pure BFO, preventing Ostwald ripening and resulting in powder with smaller crystallites and better crystallinity.

All reagents were of analytical grade and were used without further purification or treatment. Iron(III) nitrate nonahydrate [Fe(NO₃)₃*9H₂O], 99.5% purity (Merck) and bismuth nitrate pentahydrate [Bi(NO₃)₃*5H₂O], ASC 98% (Alfa Aesar) were used as starting materials. The iron and bismuth contents were experimentally determined by complexometric titration. The precursor solutions of bismuth and iron are prepared by adding stoichiometric proportions (10 mmol) of the raw materials in diluted nitric acid under heating and stirring. Gradually, 18 g of TRIS is added to the solution. The solvent is evaporated at 105 °C on a heating plate, forming a dried resin which ignites itself. The combusted resin is then ground in a mortar and calcined at temperatures between 400 and 600 °C for 1 h to eliminate secondary phases. The combustion and annealing processes were conducted in air. The asobtained powder is wet milled on a rolling bench for up to 5 days to deagglomerate the primary particles in a gentle manner without destroying the crystallites. The block diagram of the general protocol is given in Fig. S1.45

The XRD pattern of the resulting synthesis product, obtained directly after the combustion step (i.e., without any annealing) is shown in Fig. 1(a). Interestingly, the BiFeO₃ phase is already predominant, with only a few minor peaks originating mainly from the parasitic phases β -Bi₂O₃ and γ -Bi₂O₃. After an annealing step at 400 °C, those residual impurities are still present together with the α -Fe₂O₃ phase after the decrease of the amorphous background. Phase purity is then improved with temperature increase to 600 °C. Nonetheless, batch-to-batch variability was identified by the presence of differences in the impurity phases between samples. This is mainly associated with the timing and detailed



FIG. 1. (a) XRD patterns of BFO samples following the initial step of the combustion synthesis and after two subsequent annealings at 400 °C and 600 °C. Peaks denoted as *, o, and \Box belong to the parasitic phases γ -Bi₂O₃, β -Bi₂O₃, and α -Fe₂O₃, respectively, while the others are in good agreement with the BFO reference profile (ICSD#15299) shown at the bottom of the graph. (b) Schematic illustration of the BiFeO₃ structure in the hexagonal system showing one oxygen octahedron around the iron atom (Red: Fe; Brown: Bi; Blue: O, done with the CaRIne Crystallography software).

procedure of the auto ignition which is difficult to control (see for instance samples BFO-HT1 and BFO-HT2 in Fig. S2).⁴⁵ After the combustion step, powder is wet milled on a rolling bench to reduce the particle size. Representative image in Fig. 2 reveals nanoparticles without well-defined shape and typical dimension in the 100–250 nm range.

III. BFO COLLOIDAL SUSPENSION

Preparation of stable colloidal suspensions is needed for HRS studies and they are prepared using the following protocol: (i) Nanopowders are first dispersed into deionized water (pH=7) with a typical concentration of 0.4 mg/ml. (ii) Dispersions are exposed to ultrasonication for 25 min (Vibra Cell 75043, Bioblock Scientific) at a maximum input power of 750 W and a frequency of 20 kHz. A pulsed irradiation (1 s on and 4 s off) at room temperature was found to be optimal for the preparation of homogeneous dispersions.⁴⁶ (iii) Solutions are then left to settle for about one week to allow sedimentation of the larger particles and aggregates. (iv) The nanocrystal concentration at the end of the sedimentation period is estimated by weighing the residual fraction (assuming spherically shaped nanoparticles). It corresponds to 10%–30% of the initial concentration.

Typical colloidal suspensions appear yellowish (Fig. 3(b)), due to partial absorption of BFO below 600 nm.⁴⁷ Suspensions are stable with values of zeta potential below -30 mV at pH 7. Mean particle sizes were estimated by Dynamic Light Scattering (DLS) at about 100–120 nm for most of the samples as also confirmed through SEM observations (Figs. 3(a) and 3(c)). Finally, it can be noticed that the particle size and shape polydispersity are reduced after this dispersion step, a necessary improvement for correct HRS measurements.

IV. NONLINEAR OPTICAL PROPERTIES

BFO belongs to space group R3c and the SHG tensor can be described with four nonzero independent components: d_{22} , d_{15} , d_{31} , and d_{33} .⁴⁸ Very few studies have focused on the BFO optical second harmonic properties but, recently, the relative values of the d_{ij} tensor coefficients were determined at 1064 nm from single crystal measurements.⁴⁹ In another study,²² a careful determination of the absolute d_{ij}



FIG. 2. Representative TEM image of BFO particles annealed at 600 °C.



FIG. 3. (a) DLS size distribution by intensity (dashed line) and by number (full line) and (b) suspension image. (c) SEM micrograph of the particles. Scale bar is $1 \,\mu$ m.

coefficients was performed at 1550 nm in the case of both rhombohedral and strain-induced tetragonal thin films. Experimental results were found to be consistent with *ab initio* calculations.^{21,50} Interestingly, the magnitude of the coefficients of BFO appears higher than the values known for commonly used nonlinear optical materials, making BFO a very good candidate for frequency conversion applications. In addition, a significant result of this study is that a large increase of the NLO response was observed for tetragonal films in agreement with other reported enhanced properties in such films.⁵¹ In the present work, two different experimental techniques, namely HRS measurements and nonlinear polarization microscopy, were used to quantitatively assess the nonlinear optical response of BFO nanocrystals.

A. Hyper Rayleigh scattering

HRS is an ensemble measurement, well-suited to readily determine the averaged nonlinear optical coefficients of nanocrystals. This technique was applied following the procedure previously detailed for the characterization of several noncentrosymmetric oxide nanocrystals such as BaTiO₃, ZnO, LiNbO₃, and KNbO₃.^{18,52,53} HRS intensity results from the incoherent sum of the scattered SHG radiations emitted by each nanoparticle in suspension. The signal is thus proportional to the nanoparticles concentration, N, and can be expressed as

$$I_{\rm HRS} = \rm{GNT}_{np} \langle \beta_{np}^2 \rangle I_{\omega}^2.$$
(1)

Here, G is an experimental constant and T_{np} an internal field factor which is calculated according to the solvent and nanocrystal refractive indices (here, $n_{\omega} \sim 2.76$ and $n_{2\omega} \sim 3.20$ for BFO (Ref. 47)). $\langle \beta_{np} \rangle$ is the nanoparticle effective hyperpolarizability from which the averaged SHG coefficient $\langle d \rangle$ can be deduced if the nanoparticle volume V_{np} is independently estimated

$$\langle \beta_{np} \rangle = \langle d \rangle V_{np}.$$
 (2)

This expression implicitly assumes that the measured SHG signal predominantly originates from the bulk contribution thus omitting any possible surface contribution. For oxide nanomaterials, this type of behavior was already demonstrated for several nanoparticles in the 100 nm range⁵³ as well as more recently for smaller nanocrystals.^{11,15} In the above formulae, brackets indicate isotropic orientational averaging. The relation between $\langle d \rangle$ and the tensor components of BFO can be written, in our experimental configuration, as

$$\langle d^2 \rangle = \frac{6}{35} d_{33}^2 + \frac{32}{105} d_{31}^2 + \frac{8}{21} d_{22}^2 + \frac{44}{105} d_{15}^2 + \frac{4}{21} d_{31} d_{33} + \frac{4}{35} d_{15} d_{33} + \frac{16}{105} d_{31} d_{15}.$$
 (3)

Experimentally, the nanoparticle suspension was excited with a vertically polarized YAG laser ($\lambda_{\omega} = 1064 \text{ nm}$) and the scattered, unpolarized, SHG signal was detected at 90° from the laser beam axis with a photomultiplier. Calibration of the experimental set-up was previously performed with a molecular solution of para-nitroaniline as an external reference. For each sample, the HRS intensity was then measured according to the nanoparticle concentration. Quantitative values for $\langle \beta_{np} \rangle$ and $\langle d \rangle$ were finally derived from the nanoparticle concentration and size independently obtained through weighing and DLS measurements, respectively.⁵³

Fig. 4 shows a representative plot of the HRS intensity as a function of the BFO nanoparticle concentration. One can observe a deviation from the expected linear behavior



FIG. 4. HRS intensity as a function of the concentration of nanoparticles in suspension.

for the highest concentrations. This is related to the suspension absorption mostly at the second harmonic frequency.⁵³ There is however a clear linear tendency for low nanoparticle concentrations, allowing the determination of the experimental slope which is used to calculate $\langle \beta_{np} \rangle$ and $\langle d \rangle$.

Determination of these experimental parameters has been performed on four independent samples resulting from the different BFO batches (Table SI).⁴⁵ The effective hyperpolarizability is directly proportional to the nanoparticle volume (Eq. (2)) and thus varies from sample to sample. For instance, a value of $\langle \beta_{np} \rangle = 1.2.10^{-22}$ esu was found for a 110 nm particle mean size. On the contrary, the averaged coefficient $\langle d \rangle$ is an intrinsic physical property of the nanomaterial itself, which is not affected by the nanocrystal size. Experimental values range from 67 to 90 pm/V, depending on the sample, with a mean value of 79 pm/V. This variability is in line with the experimental reproducibility of the overall measurement process (estimated at $\pm 15\%$) and is mainly related to the difficulty in precisely determining the particle size from DLS, as discussed in Ref. 53. More importantly, there is no clear correlation between the type and concentration of impurities and the experimental $\langle d \rangle$ value, as long as BFO is the dominant phase in the different synthetized powders (Fig. S2 and Table SI).⁴⁵ This finding is in agreement with the hypothesis of a predominant bulk SHG contribution related to the noncentrosymmetric structure of the material. The "actual BFO nanocrystal volume" for each particle is indeed poorly affected, at first order, by the presence of minor impurity phases.

Finally, this first quantitative assessment of the NLO response of BFO nanocrystals is found to be in relatively good agreement with the d_{ij} coefficients extracted from ab initio calculations.²¹ At 1064 nm, these theoretical coefficients lead to a $\langle d \rangle$ value of 45.4 pm/V (Table SII).⁴⁵ Valuable comparative information was also gained when comparing the NLO response of BFO with previously characterized nanomaterials under the same experimental HRS setup. Interestingly, it was found for instance $\langle d \rangle = 7.4 \text{ pm/V}$ and $\langle d \rangle = 5.5 \text{ pm/V}$ for LiNbO₃ and BaTiO₃ nanocrystals, respectively.⁵³ A very good nonlinear optical efficiency is therefore demonstrated for BFO, which is typically one order of magnitude higher than for standard NLO materials.

B. Nonlinear polarization microscopy

The SHG images were acquired using an inverted laser scanning microscope (Nikon TE300), equipped with a $0.6NA 40 \times objective$. The position of the sample was controlled by an XYZ piezo-scanner with 2 nm resolution. The excitation source was a mode locked Ti:Sapphire oscillator (Synergy 20, Femtolasers), providing 20 fs pulses at 80 MHz repetition rate. The incident light polarization was selected by a rotating half wave plate, while SHG signal was epidetected using the same objective. A combination of a 650 nm blocking edge short pass filter (AHF, F37–650) and a bandpass filter (40 nm bandwidth at 400 nm) ensured an efficient rejection of the 800 nm scatter. After being analyzed by a Glan–Taylor polarization cube, the signal was measured by a photomultiplier tube and processed by a lock-in amplifier.

This article is copyrighted as indicated in the article. Reuse of AIP content is subject to the terms at: http://scitation.aip.org/termsconditions. Downloaded to] IP: 129.194.8.73 On: Wed, 17 Sep 2014 07:51:56

At first, an SHG raster scan image of a substrate with isolated nanoparticles was acquired. Then the laser beam was focused onto selected crystals. During this operation, the SHG signal was maximized by adjusting the microscope piezo-scanner displacements. The polarization response was acquired by measuring the SHG signal as a function of the polarization angle of the incident light γ and of the detection polarization, setting the analyzer along the *X* or *Y* direction (definitions in Fig. 5).

The experimental SHG polarization response was then fitted according to the following assumptions:¹ the fundamental beam is assumed to be at normal incidence, with only two in-plane components $E_x^{\omega} = E_{\omega} \cos \gamma$ and $E_y^{\omega} = E_{\omega} \sin \gamma$; the collected SHG intensity in the *X* direction I_x (or equivalently, I_y , in the Y direction) is then assumed to be proportional to $P_x^2(P_y^2)$, where *P* is the nonlinear polarization given by

$$P_i^{2\,\omega} = \varepsilon_0 \, \sum_{jk} d_{ijk} E_j^{\omega} E_k^{\omega}, \qquad (4)$$

The crystal nonlinear tensor d_{ijk} is given here in the laboratory reference frame and can be derived from the d_{mnl} tensor expressed in the crystal frame by

$$d_{ijk} = \sum_{mnl} d_{mnl} S_{im} S_{jn} S_{kl}, \tag{5}$$



FIG. 5. (a) 2D SHG image of BiFeO₃ nanocrystals. (b) Definition of the angles. The crystal orientation is expressed in the laboratory frame X, Y, Z by the Euler angles φ , θ , and ψ . The angle γ denotes the polarization of incident laser light on the sample plane. (c) and (d) Polarization emission of BiFeO₃ nanocrystals. Each signal is analyzed along two orthogonal directions: X (blue color) and Y (red color). Dots correspond to experimental data, while solid lines represent the best fit.

[This article is copyrighted as indicated in the article. Reuse of AIP content is subject to the terms at: http://scitation.aip.org/termsconditions. Downloaded to] IP: 129 194 8 73 On: Wed 17 Sep 2014 07:51:56 where S_{im} are the components of the rotation matrix between the laboratory and crystal axes depending on the Euler angles φ , θ , and ψ . Knowing d_{mnl} elements, four free parameters remain to be adjusted for the fit: the Euler angles and the experimental factor K, which accounts for the incident laser intensity, the collection and the detection efficiency and the crystal size. For the data analysis, the polarization response of the dichroic mirror and the objective was also taken into account.

Currently in the literature, a few different sets of relative d_{ij} values for BFO are present, as reported in Table SII.⁴⁵ The first set (set 1) was derived from BFO single crystal measurements⁴⁹ at 1064 nm, the second (set 2)⁴⁷ and third $(set 3)^{22}$ were obtained from BFO thin film measurements at 800 nm and 1550 nm, respectively. A fourth set (set 4) can also be obtained from *ab initio* simulation.²¹ Although Haislmaier et al.²² correctly pointed out that the set 2 of d_{ij} values does not account for absorption at 400 nm, this set, which was derived for 800 nm excitation, is the only one which allowed us to fit our experimental results as shown in Fig. 5. Two representative results are shown in panel 5(c)and 5(d), as results of the experimental fitting indicated above, and the same fitting procedure yielded similar agreement on all the particles in the sample except for large agglomerates.¹ It can be noticed that only the relative d_{ii} coefficients are involved in the fitting procedure. We thus find that the relative d_{ij} values of set 2 correctly fit our experimental response. However, it is to be pointed out that the averaged <d> coefficient computed from the individual tensor components given in Ref. 47 exceeds by two orders of magnitude our estimation based on HRS measurements (Table SII).⁴⁵

V. MAGNETIC PROPERTIES

Room temperature magnetic response, measured by vibrating sample magnetometry, for a BFO sample annealed at 350 °C is shown in Fig. 6(a) (sample BFO-LT2 in Table SI).⁴⁵ A clear ferromagnetic behavior is measured with a relatively high saturation magnetization at 3.5 emu.g^{-1} . This



FIG. 6. (a) Room temperature magnetic hysteresis loops of BFO sample BFO-LT2. (b) Magnetic separation of BFO particles in water suspension.

can be related to the presence of impurities.^{24,44} Pure BFO nanoparticles only display weak ferromagnetism, with saturation magnetization of about 1 emu.g⁻¹, when the particle size is below the period of the spiral spin structure at 62 nm.^{23,54} On the other hand, stronger magnetic responses were already reported and traced to iron oxide impurities (it is worth noting that this behavior has already been seen in samples prepared by combustion synthesis).⁴⁴ This is in agreement with the XRD analysis presented in this work that clearly shows the presence of the γ -Fe₂O₃ phase in the sample, as shown in Fig. S2.⁴⁵

Moreover, it should be pointed out that the SHG properties of the BFO particles are not affected by the presence of small quantities of impurity phases. For instance, the nonlinear $\langle d \rangle$ coefficient of the BFO-LT2 sample is 84 pm/V, in agreement with other samples in this study. Thus, it shows that careful synthesis optimization can promote both second harmonic efficiency and high magnetic properties. This latter is useful for magnetic separation, for instance, as shown in Fig. 6(b). Therefore, the multimodal potential of the particles presented in this work could be advantageously applied for specific biomedical applications.

VI. CONCLUSION

BFO nanoparticles were prepared by the combustion method and their SHG properties were then determined through HRS and nonlinear polarization microscopy. The high SHG efficiency, with a $\langle d \rangle$ coefficient measured at $79 \pm 12 \text{ pm/V}$, confirms that BFO is a promising material for frequency conversion applications. We additionally demonstrated that the nanoparticles SHG properties are not quenched when small quantities of impurities are present. This is due to the bulk nature of the second harmonic process occurring within BFO particles. Moreover, moderate ferromagnetic response was observed for nanoparticles containing residual γ -Fe₂O₃ impurities, allowing the particles to be magnetically separated in solution. BFO nanoparticles are therefore new promising HNPs combining a very high SHG brightness and a moderate magnetic response. Finally, their cytotoxicity and internalization mechanism were carefully evaluated in Ref. 55, showing that they have good biocompatibility and are suitable for a wide range of bio-imaging and diagnostic applications.

ACKNOWLEDGMENTS

This research was partially supported by a European FP7 Research Project NAMDIATREAM (NMP4-LA-2010-246479, http://www.namdiatream.eu) and by a PHC Ulysses program (32032WG). The authors thank Michel Moret for the help with the design of mechanical components of the microscope involved in nonlinear microscopy measurements.

¹L. Bonacina, Y. Mugnier, F. Courvoisier, R. Le Dantec, J. Extermann, Y. Lambert, V. Boutou, C. Galez, and J.-P. Wolf, Appl. Phys. B **87**, 399 (2007).

[This article is copyrighted as indicated in the article. Reuse of AIP content is subject to the terms at: http://scitation.aip.org/termsconditions. Downloaded to] IP 129.194.8.73 On: Wed. 17 Sep 2014 07:51:56

²M. Zielinski, D. Oron, D. Chauvat, and J. Zyss, Small 5, 2835 (2009).

³A. V. Kachynski, A. N. Kuzmin, M. Nyk, I. Roy, and P. N. Prasad, J. Phys. Chem. C **112**, 10721 (2008).

- ⁴L. Le Xuan, C. Zhou, A. Slablab, D. Chauvat, C. Tard, S. Perruchas, T. Gacoin, P. Villeval, and J.-F. Roch, Small 4, 1332 (2008).
- ⁵C.-L. Hsieh, R. Grange, Y. Pu, and D. Psaltis, Opt. Express 17, 2880 (2009).
- ⁶P. Pantazis, J. Maloney, D. Wu, and S. E. Fraser, Proc. Natl. Acad. Sci., U.S.A. **107**, 14535 (2010).
- ⁷J. Extermann, L. Bonacina, E. Cuña, C. Kasparian, Y. Mugnier, T. Feurer, and J.-P. Wolf, Opt. Express 17, 15342 (2009).
- ⁸W. P. Dempsey, S. E. Fraser, and P. Pantazis, BioEssays **34**, 351 (2012). ⁹L. Bonacina, Mol. Pharm. **10**, 783 (2013).
- ¹⁰R. Ladj, M. El Kass, Y. Mugnier, R. Le Dantec, H. Fessi, C. Galez, and A. Elaissari, Cryst. Growth Des. **12**, 5387 (2012).
- ¹¹B. Knabe, K. Buse, W. Assenmacher, and W. Mader, Phys. Rev. B 86, 195428 (2012).
- ¹²A. Sergeyev, R. Geiss, A. S. Solntsev, A. Steinbrück, F. Schrempel, E.-B. Kley, T. Pertsch, and R. Grange, Opt. Express **21**, 19012 (2013).
- ¹³Y. Nakayama, P. J. Pauzauskie, A. Radenovic, R. M. Onorato, R. J. Saykally, J. Liphardt, and P. Yang, Nature 447, 1098 (2007).
- ¹⁴L. Mayer, A. Slablab, G. Dantelle, V. Jacques, A.-M. Lepagnol-Bestel, S. Perruchas, P. Spinicelli, A. Thomas, D. Chauvat, M. Simonneau, T. Gacoin, and J.-F. Roch, Nanoscale 5, 8466 (2013).
- ¹⁵E. Kim, A. Steinbrück, M. T. Buscaglia, V. Buscaglia, T. Pertsch, and R. Grange, ACS Nano 7, 5343 (2013).
- ¹⁶B. E. Urban, P. B. Neogi, S. J. Butler, Y. Fujita, and A. Neogi, J. Biophoton. 5, 283 (2012).
- ¹⁷S. Winter, M. Zielinski, D. Chauvat, J. Zyss, and D. Oron, J. Phys. Chem. C **115**, 4558 (2011).
- ¹⁸D. Staedler, T. Magouroux, R. Hadji, C. Joulaud, J. Extermann, S. Schwung, S. Passemard, C. Kasparian, G. Clarke, M. Gerrmann *et al.*, ACS Nano 6, 2542 (2012).
- ¹⁹A. M. Derfus, W. C. W. Chan, and S. N. Bhatia, Nano Lett. 4, 11 (2004).
- ²⁰D. Lebeugle, D. Colson, A. Forget, and M. Viret, Appl. Phys. Lett. **91**, 022907 (2007).
- ²¹S. Ju, T.-Y. Cai, and G.-Y. Guo, J. Chem. Phys. 130, 214708 (2009).
- ²²R. C. Haislmaier, N. J. Podraza, S. Denev, A. Melville, D. G. Schlom, and V. Gopalan, Appl. Phys. Lett. **103**, 031906 (2013).
- ²³T.-J. Park, G. C. Papaefthymiou, A. J. Viescas, A. R. Moodenbaugh, and S. S. Wong, Nano Lett. 7, 766 (2007).
- ²⁴R. Guo, L. Fang, W. Dong, F. Zheng, and M. Shen, J. Mater. Chem. 21, 18645 (2011).
- ²⁵R. Mazumder, P. S. Devi, D. Bhattacharya, P. Choudhury, A. Sen, and M. Raja, Appl. Phys. Lett. **91**, 062510 (2007).
- ²⁶J. Gao, H. Gu, and B. Xu, Acc. Chem Res. **42**, 1097 (2009).
- ²⁷D. Staedler, T. Magouroux, S. Passemard, S. Schwung, M. Dubled, G. S. Schneiter, D. Rytz, S. Gerber-Lemaire, L. Bonacina, and J.-P. Wolf, Nanoscale 6, 2929 (2014).
- ²⁸M. I. Morozov, N. A. Lomanova, and V. V. Gusarov, Russ. J. Gen. Chem. 73, 1676 (2003).
- ²⁹S. M. Selbach, M.-A. Einarsrud, and T. Grande, Chem. Mater. 21, 169 (2009).
- ³⁰N. Birks, G. H. Meier, and F. S. Pettit, *Introduction to the High Temperature Oxidation of Metals* (Cambridge University Press, 2006).

- ³¹J.-T. Han, Y.-H. Huang, X.-J. Wu, C.-L. Wu, W. Wei, B. Peng, W. Huang, and J. B. Goodenough, Adv. Mater. 18, 2145 (2006).
- ³²L. Wu, C. Dong, H. Chen, J. Yao, C. Jiang, and D. Xue, J. Am. Ceram. Soc. **95**, 3922 (2012).
- ³³G. Biasotto, A. Z. Simões, C. R. Foschini, M. A. Zaghete, J. A. Varela, and E. Longo, Mater. Res. Bull. 46, 2543 (2011).
- ³⁴C. Goia, E. Matijević, and D. V. Goia, J. Mater. Res. **20**, 1507 (2005).
- ³⁵C. Feldmann and H.-O. Jungk, Angew. Chem. Int. Ed. **40**, 359 (2001).
- ³⁶D. Maity, S. N. Kale, R. Kaul-Ghanekar, J.-M. Xue, and J. Ding, J. Magn. Magn. Mater. **321**, 3093 (2009).
- ³⁷E. A. V. Ferri, I. A. Santos, E. Radovanovic, R. Bonzanini, and E. M. Girotto, J. Braz. Chem. Soc. **19**, 1153 (2008).
- ³⁸X. Wang, Y. Zhang, and Z. Wu, Mater. Lett. **64**, 486 (2010).
- ³⁹Y. Hu, L. Fei, Y. Zhang, J. Yuan, Y. Wang, and H. Gu, J. Nanomaterials 2011, Article ID 797639 (2011).
- ⁴⁰M. P. Pechini, US Patent 3,330,697 (1967).
- ⁴¹K. C. Patil, S. T. Aruna, and S. Ekambaram, Curr. Opin. Solid State Mater. Sci. 2, 158 (1997).
- ⁴²K. C. Patil, S. T. Aruna, and T. Mimani, Curr. Opin. Solid State Mater. Sci. 6, 507 (2002).
- ⁴³S. Farhadi and M. Zaidi, J. Mol. Catal. Chem. 299, 18 (2009).
- ⁴⁴S. Vijayanand, H. S. Potdar, and P. A. Joy, Appl. Phys. Lett. **94**, 182507 (2009).
- ⁴⁵See supplementary material at http://dx.doi.org/10.1063/1.4895836 for block diagram of the synthesis, BFO samples used for optical and/or magnetic characterizations and literature values of BFO nonlinear coefficients.
- ⁴⁶V. S. Nguyen, D. Rouxel, R. Hadji, B. Vincent, and Y. Fort, Ultrason. Sonochem. 18, 382 (2011).
- ⁴⁷A. Kumar, R. C. Rai, N. J. Podraza, S. Denev, M. Ramirez, Y.-H. Chu, L. W. Martin, J. Ihlefeld, T. Heeg, J. Schubert, D. G. Schlom, J. Orenstein, R. Ramesh, R. W. Collins, J. L. Musfeldt, and V. Gopalan, Appl. Phys. Lett. **92**, 121915 (2008).
- ⁴⁸R. L. Sutherland, *Handbook of Nonlinear Optics* (Marcel Dekker, 2003).
- ⁴⁹H. Yokota, R. Haumont, J.-M. Kiat, H. Matsuura, and Y. Uesu, Appl. Phys. Lett. **95**, 082904 (2009).
- ⁵⁰S. Ju and T.-Y. Cai, Appl. Phys. Lett. **95**, 112506 (2009).
- ⁵¹R. J. Zeches, M. D. Rossell, J. X. Zhang, A. J. Hatt, Q. He, C.-H. Yang, A. Kumar, C. H. Wang, A. Melville, C. Adamo, G. Sheng, Y.-H. Chu, J. F. Ihlefeld, R. Erni, C. Ederer, V. Gopalan, L. Q. Chen, D. G. Schlom, N. A. Spaldin, L. W. Martin, and R. Ramesh, Science **326**, 977 (2009).
- ⁵²R. Le Dantec, Y. Mugnier, G. Djanta, L. Bonacina, J. Extermann, L. Badie, C. Joulaud, M. Gerrmann, D. Rytz, J. P. Wolf, and C. Galez, J. Phys. Chem. C 115, 15140 (2011).
- ⁵³C. Joulaud, Y. Mugnier, G. Djanta, M. Dubled, J.-C. Marty, C. Galez, J.-P. Wolf, L. Bonacina, and R. Le Dantec, J. Nanobiotechnol. **11**, S8 (2013).
- ⁵⁴F. Huang, Z. Wang, X. Lu, J. Zhang, K. Min, W. Lin, R. Ti, T. Xu, J. He, C. Yue, and J. Zhu, Sci. Rep. 3, Article No. 2907 (2013).
- ⁵⁵D. Staedler, S. Passemard, A. Rogov, C. Manus Maguire, B. M. Mohamed, S. Schwung, D. Rytz, T. Jüstel, S. Hwu, Y. Mugnier, R. Le Dantec, Y. Volkov, S. Gerber-Lemaire, L. Bonacina, and J.-P. Wolf, "Cellular uptake and biocompatibility of bismuth ferrite harmonic advanced nanoparticles," Nanomedicine (submitted).